

Grade	Value	Unit
Reaction to fire	Class A1	
Dry bulk density	$\leq 1,600$	kg/m ³
Compressive strength	CS IV	
Water absorption	Class W0	
Water vapour transmission, μ (EN 12086)	≤ 15	
Adhesion	≥ 0.08	N/mm ² FP B
Thermal conductivity, $\lambda_{10 \text{ dry}}$ (average tabular value; P=50%)	0.61	W/m×K

Data are average results of tests conducted under standard procedures and are subject to variation.

Data contained in this data sheet are supplied in good faith as a technical service and are subject to change without notice. Misprint and errors excepted.

Revision number: 14-03-2018